



# Aquabond RSD 3801

Product Data Sheet

## Description

SABA Aquabond RSD 3801 is a two-component water-based sprayable adhesive for the foam converting industry. SABA Aquabond RSD 3801 is ideal for the production of comfort- and project furniture.

## Special properties

- Solvent-free
- Direct adherence to smooth, non-porous surfaces
- No drying time
- Very high initial tack

## Method of use

Apply by a two-component spray gun. Please spray both parts, assemble parts within 8 minutes and press well. SABA Aquabond RSD 3801 must be used in combination with SABA Activator 3739. For more detailed information see the SABA Activator 3739 product sheet. Spraying pressure about 2 bar and spraying distance at least 30 cm.

## Technical data

Viscosity at 23 °C	: approx. 1,020 mPa.s
Density	: approx. 1,105 kg/m <sup>3</sup>
Solids content	: approx. 52%
Open time	: two sides approx. 8 minutes
Curing time	: approx. 24 hours
Coverage	: approx. 70-100 g/m <sup>2</sup> , depending on application
Clean with	: SABA Cleaner AV
Work temperature	: minimum + 15 °C
Storage temperature	: minimum + 5 °C and maximum + 35 °C (frost sensitive)
Temperature resistance	: approx. + 55 °C
Shelf life	: 6 months in unopened packing

## Order information

Packing	: 20 litres jerrycan, contents 22 kg 200 litres drum, contents 216 kg 1,000 litres IBC container, contents 1,050 kg
Colours	: natural, blue and pink

## Safety recommendations

See the corresponding material safety data sheet.

## SABA Dinxperlo BV

Industriestraat 3, NL-7091 DC Dinxperlo, PO Box 3, NL-7090 AA Dinxperlo, the Netherlands, Tel +31 (0) 315 658999, Fax +31 (0) 315 653207, E-mail [info@saba.nl](mailto:info@saba.nl), Internet [www.saba.nl](http://www.saba.nl).

*Our recommendations and instructions for use are based on the present status of know-how and technique. Clients and users should evaluate our products by themselves, with regard to utilization and requirements of their own choice. We shall take no responsibility in case our products are not being used subject to our recommendations and/or instructions for use. Furthermore, General Terms and Conditions of the Dutch Association "Nederlandse Vereniging van Rubber en Kunststoffabrikanten of November 1, 1992", will apply to our recommendations, instructions for use and the delivery of our products.*

Version: 2008-08-25